



FLR.0083

**OSMOKOLL**

Osmotic two-component type weatherstrip adhesive cement

### **Customs Code**

3824 5090

### **Packaging**

- Bag 25 kg [A]
- Plastic can 4 kg [B]
- Kit: 1 Bag 25 kg [A] + 1 Plastic can 4 kg [B]

### **Application**

- Notched finishing trowel

Family  
**Floortech**

Product Lines  
• Aqua  
• Building

Components  
**Two-components**

Type  
**Adhesive and putty for flooring**

Functional Categories  
• **Bonding and filling tiles, parquet, etc.**  
• **Osmotic waterproofing**

Appearance  
**Powder + Liquid**

## Certifications and legislations



**EN 998-1**

Specification for Mortar for Masonry - General purpose rendering/plastering mortar (GP)

## General description

Two-component adhesive cement for interior and exterior use, based on hydraulic binders, modifying and flexibilising resins, selected siliceous aggregates, for the preparation of adhesive mixtures, easy to spread, with high deformation capacity and watertightness. Perfect for bonding coatings even low absorption, on cement surfaces with low porosity (for example interior coverings for swimming pools).










## Dosage

Use from 5 to 6 kg/m<sup>2</sup> of OSMOKOLL depending on the type of support and the type of material to be bonded.

## Fields of application

Bonding tiles, waterproofing and anti-humidity coatings, structures and masonry exposed or underground provided they are sufficiently porous and absorbent and free from any waterproofing and / or water-repellent surface treatment, whether chemical (siloxanes, epoxies, polyurethanes, etc.) or natural (wax-up). Bonding small vitreous tiles for swimming pools. Bonding tiles on OSMOCEM FLEX or OSMOCEM D type osmotic coatings on terraces and balconies.

## Basic features

- |   |   |
|---|---|
|  Max. recommended thickness:<br>5 mm   |  Maximum diameter of aggregate:<br>0.4 mm |
|  Min. recommended thickness:<br>2.5 mm |  Nonflammable                             |
|  Pot-life:<br>50 min                   |  Shelf-life:<br>12 months                 |
|  Temperature of use:<br>+5 / +35 °C    |  UV-resistant                             |
|  Available colours<br>Gray             |   |

## Technical specifications

*Bonding force (UNI EN 1542): 2.8 N/mm<sup>2</sup>*

*Capillary absorption (UNI EN 1015-18): 0.08 kg•h<sup>0.5</sup>/m<sup>2</sup>*

*Complete hardening (a 20°C): 80 - 90 min*

*Compressive strength (UNI EN 1015-11): 40 N/mm<sup>2</sup>*

*Density (UNI EN 1015-6): 2.050 N/mm<sup>2</sup>*

*Mixing ratio of the components A:B: 4.8:1 \_*

IF YOU WANT TO SOLVE IT  


[www.azichem.com](http://www.azichem.com)

Updated: **24/08/2020**

General sales conditions and legal notices on

[www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)

## Tools cleansing

- Water

## Applicable on

- Concrete
- Tiles
- Floor screed

## Substrate preparation

Application surfaces should be clean, free of soiling, crumbling and non-adhering parts, dust, etc., water repellent treatments in general, etc. conveniently saturated with water until they reach the condition "saturated with dry surface".

## Instructions for use

Mix the powder component (component A) with the hydrating solution (component B) with a drill at a low number of revolutions, pouring the powder progressively in the liquid, continue mixing until a homogeneous lump-free mixture is obtained. After mixing is completed wait a few minutes and stir again before proceeding with the application.

## Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



## Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: [www.azichem.com](http://www.azichem.com). The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: [www.azichem.com](http://www.azichem.com).

It is forbidden to dispose of the product and/or packaging in the environment.

It is always essential to carry out preliminary tests to verify the appropriateness of the product, depending on specific requirements.

Do not apply in case of direct exposure to sunlight and cure the protection and moist hardening.

Do not apply on little or non-porous substrates or previously coated with water-repellent treatments in general, if not after appropriate roughening by bush hammers, sanders and equipment suitable for preparatory treatments of substrates, or after appropriate treatment with suitable polymeric primers.

*OSMOKOLL is produced/distributed by*



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy  
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



[www.azichem.com](http://www.azichem.com)

Updated: **24/08/2020**  
General sales conditions and legal  
notices on  
[www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)