



Family  
Grout

Type  
Fluid cement-based or hydraulic lime based grouts and micro mortars

Product Lines  
• Opus  
• Sanageb

Functional Categories  
• Structural strengthening of masonry in historic buildings  
• Roads and municipal maintenance interventions

Components  
Single-component

Appearance  
Powder

GRT.0154

## SANAFLUENS

Superfluid grout based on reinforcing, injectable hydraulic lime mortar

### Customs Code

3824 5090

### Packaging

- Bag 25 kg
- Pallet: 50 x (Bag 25 kg)

### Application

- Injection
- Pour out
- Pump

## Certifications and legislations



EN 998-2

Masonry mortars - Masonry mortar for general purposes (G)

## General description

Powder preparation, ready-to-use, based on hydraulic lime, for the preparation, with the sole addition of water, of grout for masonry reinforcement, injectable and castable, high performance in terms of sliding, strength and stability, for ecological building interventions and the restoration of vintage buildings and monuments.

## General features

In the SANAFLUENS mixtures, the water is completely and stably incorporated from the hydration reaction of lime; conversely, in traditional mixtures, a very high part of added water, is free, and evaporating, it leaves gaps in the walls.

SANAFLUENS is based on natural hydraulic lime, sodium gluconate, kaolin, aluminates; it does not contain cement, resins, solvents and radioemissive aggregates.

## Dosage

Approximately 1500 kg of SANAFLUENS for each cubic metre of volume to be filled.

## Fields of application

Wall reinforcements of "bag" masonry or masonry damaged by earthquake by injections.

## Basic features



Dosage:  
1.50 - 1.55 kg/dm<sup>3</sup>



Mix with water:  
22-24 %



Pot-life:  
60 min



Shelf-life:  
12 months



Temperature of use:  
+6 / +30 °C



Available colours  
Gray

## Technical specifications

Bonding force (UNI EN 1015-12): 1.2 N/mm<sup>2</sup>

Capillary absorption (UNI EN 1015-18): 0.53 kg•h<sup>0.5</sup>/m<sup>2</sup>

Chloride content (UNI EN 1015-17): 0.0082 %

Compressive strength (UNI EN 1015-11): > 20 N/mm<sup>2</sup>

Density (UNI EN 1015-6): 1980 kg/m<sup>3</sup>

Flexural strength (UNI EN 1015-11): > 6 N/mm<sup>2</sup>

Permeability to water vapor (EN 1745): 15/35 μ

Static elastic modulus: 12000 MPa

Thermal conductivity (EN 1745): 0.67 W/m\*K



www.azichem.com

Updated: 24/08/2020

General sales conditions and legal notices on

www.azichem.com/disclaimer

## Tools cleansing

- Water

## Applicable on

- Bricks
- Mixed walls (bricks and stones)
- Stone walls

## Substrate preparation

Clean the surfaces of application by spraying water abundantly. In the case of lack of plaster, apply a suitable hydraulic lime and sand (type UNTERSANA) rendering to close escape routes of the injected grout as much as possible. Draw a square lattice of 50 cm. from the bottom upwards and from left to right. At the intersection of the panels, perforate the masonry with a professional drill, with a tip of at least 22 mm in diameter, with a depth of at least 3/5 of its thickness, tilting the drill by about 20° downward. Once all the holes have been drilled, spray them with water to remove the dust inside them, produced by drilling. Insert the transparent rubber hoses in the holes to a depth of about 5 cm, letting them protrude the hole by at least 35-40 cm. Appropriately seal the hole containing the tube (with cement stucco).

## Instructions for use

Pour about 2/3 of the mixing water into the mixer. Gradually add SANAFLENS and the water still required, continue to mix until a fluid, homogeneous, lump-free grout of the desired consistency is obtained. The mixing water indicatively necessary is equal to 22-24% by weight (5.5 - 6 litres per bag).

Reinforcing backfills and fills can be carried out both by gravity and using manual or automatic pumps, depending on the type of application. To verify the effectiveness of the reinforcement, the grout will come out of the pipes adjacent to that in which it is injected.

## Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



## Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: [www.azichem.com](http://www.azichem.com). The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: [www.azichem.com](http://www.azichem.com).

It is forbidden to dispose of the product and/or packaging in the environment.

An abundant preliminary injection of water into the holes drilled in the masonry is recommended, to allow an adequate and rapid sliding of the grout.

*SANAFLUENS is produced/distributed by*



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy  
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



[www.azichem.com](http://www.azichem.com)

Updated: **24/08/2020**  
General sales conditions and legal  
notices on  
[www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)