



Family
Intotech

Type
Hydraulic lime based plasters

Product Lines
• **Building**
• **Opus**
• **Sanageb**

Functional Categories
• **Renewal of wet masonry with waterproofing plasters**
• **Thermal-insulating renewal of masonry**

Components
Single-component

Appearance
Powder

INT.0011

CALEOSANA

Insulating, macroporous,
dehumidifying, anti-condensation
plaster

Customs Code

3824 5090

Packaging

- Bag 25 kg

Application

- Finishing trowel
- Brick trowel
- Plastering machine
- Straight edge

Certifications and legislations



EN 998-1

Specification for Mortar for Masonry - Mortars for renovations (R)

General description

Macroporous, ecological, high-thermo-insulating performance indoor and outdoor plaster, with density 800 kg/m³, based on hydraulic lime, botticino, siliceous aggregates, kaolin, calcium caseinate, Vichy salt, tartaric acid, expanded granular clay, natural fibres, granular perlite. Its peculiar characteristics make it suitable for dehumidification, for heat and humidity treating buildings and walls, in ecological building interventions and in the restoration of vintage buildings and monuments.

General features

CALEOSANA does not contains traces of resins, solvents or radioemissive aggregates.

Dosage

Approximately 9 kg/m² of CALEOSANA for every centimetre of thickness to be implemented (approximately 900 kg per cubic metre).

Fields of application

Vintage and new construction masonries subject to rising damp, condensation, mildew. Recommended mainly for thermo-insulating anti-condensation rehabilitation of internal perimetral masonry and underground areas in general.

Basic features



Maximum diameter of aggregate:
2 mm

A:B Mixing ratio:
22 - 24 %



Pot-life:
90 min



Shelf-life:
12 months



Available colours
Light gray

Technical specifications

Bonding force (UNI EN 1015-12): 0.40 N/mm²

Capillary absorption (UNI EN 13057): 0.83 kg•h^{0.5}/m²

Compressive strength (UNI EN 1015-11): > 5 N/mm²

Density (UNI EN 1015-6): 1075 kg/m³

Flexural strength (UNI EN 1015-11): > 2 N/mm²

Permeability to water vapor (UNI EN 1015-19): < 10 μ

Reaction to fire (EN 13501-1): A1 _

Static elastic modulus (EN 13412): < 5000 N/mm²

*Thermal conductivity (EN 1745): 0.2 W/m*K*

IF YOU WANT TO SOLVE IT


www.azichem.com

Updated: **24/08/2020**

General sales conditions and legal
notices on

www.azichem.com/disclaimer

Tools cleansing

- Water

Applicable on

- Concrete
- Bricks
- Tuff
- Mixed walls (bricks and stones)
- Brickworks
- Stone walls

Substrate preparation

Removal of degraded plaster up to the ceiling. Cleaning the resulting supports, including the removal of salt deposits; thorough dedusting and saturation with water, to obtain the condition "saturated with dry surface".

Instructions for use

In the presence of salt efflorescence brush thoroughly and spray the saline inhibitor SANAREG. If necessary, to increase plaster adhesion, apply a breathable anchoring scratch coat made with the specific lime-based preparation UNTERSANA. Prepare the plaster by adding CALEOSANA to the mixing water, continue to mix until the desired mixture and the complete elimination of lumps is obtained. Apply with float and trowel or plastering pump. It is recommended to apply a minimum thickness of cm 2.5. Regularisation of the plastered surfaces with SANASTOF lime-based ecological building fine mortar.

UNTERSANA rendering, applied by "spraying", must provide a rough, corrugated surface, designed to promote the bonding of the subsequent plaster, which must be applied no later than 2-3 days. For thicknesses greater than 2.5 cm, to improve the anti-cracking capacity, ensure the ARMAGLASS 160 mesh is inserted.

Protect fresh surfaces from direct exposure to the sun, the rain and the wind, cure the prolonged moist hardening.

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity. Store the product at a temperature between +5°C and +35°C.



www.azichem.com

Updated: **24/08/2020**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

CALEOSANA is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **24/08/2020**
General sales conditions and legal
notices on
www.azichem.com/disclaimer