



RDM.0220

READYMESH MX-500

High performance 50mm steel
fibres

🚚 Customs Code

7326 2000

📦 Packaging

- Bag 20 kg
- Pallet: 50 x (Bag 20 kg)

Family
Readymesh

Product Lines
• Infratech
• Floor

Components
Single-component

Type
Steel fibres for concrete

Functional Categories
• **Improvement of mechanical and/or rheological performance of newly manufactured mortars, plasters and concretes**
• **Construction of high performance industrial concrete floors**
• **Prefabrication**

Appearance
Fibers

Certifications and legislations



EN 14889-1:2006 (System 1)

Fibres for concrete - Steel fibres - Definitions, specification and conformity

General description

READYMESH MX-500 is a special carbon steel fibre, obtained by the extrusion and cutting of high-strength steel wire. Its special double-hooked form gives it a remarkable shear strength, thus conferring the concrete with excellent post-cracking structural strength even at low doses. READYMESH MX-500 significantly increases the mechanical performance of the structure in terms of toughness, ductility, fatigue, dynamic stress, shock, wear, tensile and shear strength and even post-cracking and damage behaviour.

Fields of application

General preparation of fibre-reinforced concrete with high pre and post-cracking performance. Ideal for industrial flooring and prefabrications.

Basic features



Density:
7.8 kg/dm³



Diameter:
0.75 mm



Double hook geometry



Length:
50 mm



Unlimited shelf-life



Use wearing protective gloves



UV-resistant



Available **colours**
Steel

Technical specifications

Aspect ratio (l / d): 67 _

Breaking load longitudinal: 1100 N/mm²

Effective length: 54.5 mm

Linear development (12 kg/m³): 3270 m/m³

Nominal length: 50 mm

Non-toxic material

Number of filaments: 5000 nr/kg

Static elastic modulus: 210000 N/mm²



www.azichem.com

Updated: **15/02/2021**

General sales conditions and legal notices on

www.azichem.com/disclaimer

Instructions for use

"READYMESH MX-500 fibres must be added to the concrete during mixing. It is recommended to pour the fibres directly onto the loading belt of the concrete mixer during the loading of the aggregates. Alternatively, it is possible to add them directly into the mixer after loading the concrete. In this case, add the fibres a little at a time so that they are well-distributed in the cement mix and extend the mixing time by at least one minute for every 20 kg of fibres added in order to achieve optimal distribution.

Conglomerates with READYMESH MX-500 can be easily transported and used with pumps, joiners, vibratory finishing machines, roadway extruders (e.g. slipform paver), etc."



Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

READYMESH MX-500 is produced/distributed by



www.azichem.com

Updated: **15/02/2021**
General sales conditions and legal notices on www.azichem.com/disclaimer



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398